

Note on English translation:

This is a translation of the technical data sheet valid in Iran.

All stated details and properties are in compliance with the regulations of the Iran standards and building regulations. They are only applicable for the specified products, system components, application rules, and construction details in connection with the specifications of the respective certificates and approvals. Kplus denies any liability for applications outside of Iran as this requires changes acc. to the respective national standards and building regulations.



Technical Data Sheet

2021-2022

MP ULTRA

Machine-applied gypsum plaster

Product description

Projection plaster MP ULTRA is light and particularly efficient premixed gypsum plaster based dry mortar with special light aggregates for smoothed interior surfaces.

Storage

Store the bags on wooden pallets in a dry environment. The product can be stored for 6 months. Seal damaged and opened bags airtight and use them up to 7 days.

Standards referred to

ISIRI 12015-1 and EN 13279-1 category B4/50/2, the product is subject to initial type testing and continuous factory production control.

Properties and added value

- For interiors
- Mineral-based
- Light and high yield
- Establishes a comfortable and healthy room atmosphere
- Regulates moisture and is diffusion permeable
- Fire protection effective
- Abrasion-resistant and nail-proof
- Hand or machine application

Field of application

Plaster for creation of smoothed, freely-structured or levelled surfaces for interior walls and ceilings. As a single-layer plaster for all kinds of masonry, concrete as well as stable plasterable substrates.

- From the cellar right up to the roof, suitable for all rooms with usual levels of room humidity including domestic kitchens and bathrooms (e.g. WCs in schools and bathrooms in hotels, hospitals, residential-care and nursing homes)
- As a substrate for tiles, finishing plasters, coatings or wallpapers
- For the provision of surfaces in quality levels
 - Q1 to Q3 levelled
 - Q1 to Q4 smoothed
 - Q4 smoothed

Application

Substrate and pretreatment

Clean the substrate of dust and loose parts and remove, ensure that the surface is smooth. All substrates must be stable, dry, even and free of grease and dust as well as free of any residual substances that may reduce the adhesion.

Preparation

Cover easily-soiled building components before commencement in accordance. Preparation of the substrate in accordance with the table «Substrate and pretreatment». Ensure that the drying time for the preliminary / primer coats is observed before continuing work.

Using the plaster base, correctly applied and/or pretreated concrete substrates with a residual moisture of up to 6% by weight and a substrate temperature $\geq +2^{\circ}\text{C}$ can be plastered.

Machines / equipment

Mixing pump G4 / G5

- | | |
|-------------------------------|------------|
| ■ Stator | D6-3 |
| ■ Rotor | D6-3 |
| ■ Mortar hoses | Ø 25 mm |
| ■ Wet mortar pumping distance | up to 30 m |

Mixing

Manual application

Mix the contents of one bag with approx. 19 litres of clean water without further additions using an agitator until an application-ready consistence is achieved.

Machine application

Adjust the water feed to achieve a lean mortar consistence (approx. 1 bar /metre mortar hose). Depending on the temperature, breaks in spraying not exceeding 10 to 15 minutes are possible. Clean the machine and hoses with longer breaks / interruptions in application.

Application

In order to create a level surface, spread the thrown-on / applied or machineapplied material flush and perpendicular with a H-straight edge. After initial setting has commenced, level with a feather edge and align the corners. If required, the surface can be re-worked with a wide spatula. After wetting the plaster surface with a sponge float, create enough plaster sludge and smoothen and sponge minor unevenness. After the plaster surface has set lightly, smoothen it with a wide spatula or finishing trowel. On non-frictionally bonded components between the wall and ceiling, reveal connections, etc. the separation must be continued with a separation (trowel) cut in the plaster layer. Separating strip is recommended instead of a separation cut.

Drying

Provide good ventilation to ensure quick drying of the plaster. The drying time at 10 mm plaster thickness is an average of 14 days depending on the humidity, temperature and ventilation of the room. The drying time will be extended with unsuitable temperatures / air humidity. If mastic asphalt screed is applied after plastering, sufficient transverse ventilation is required to avoid thermal stresses.

Plaster thickness

Single- or double-layer: 8 to 40 mm

Single-layer 8 to 20 mm

Average plaster thickness 10 mm, minimum plaster thickness 8 mm.

Cover tape conduits by min. 5 mm.

In special cases, a plaster thickness of up to 20 mm can be applied in a single-layer to a wall, however, application of 2 layers should be considered when the plaster thickness exceeds 20 mm, as there is an increased drying time before further coatings can be applied with a single-layer. The overall drying time is reduced when the first plaster layer dries more quickly.

Double-layer \geq 20 to 40 mm

Roughen the first layer with a trapezoid metal sheet or similar and apply suitable primer when fully dry. The next layer can be applied after the first layer is fully dry.

(Concrete) Ceilings

may only be plastered as a single-layer and a maximum plaster layer of 10 mm.

EPS boards and sheathing blocks as well as wood wool lightweight boards should have a single-layer applied and the entire surface must be reinforced (see reinforcement).

Minimum plaster thickness 10 mm.

Substrate for tiling

Application as a single-layer in a minimum plaster thickness of 10 mm. Level and roughen wall surfaces after application. Do not smoothen or sponge the surface.

Allow to dry and set fully before priming and applying a tile covering. In non-commercial bathrooms and kitchens (e.g. WCs in schools, bathrooms in hotels, hospitals, residential-care and nursing homes) as substrates for tiles and floor slabs, if the weight of the tiles and floor slabs including the thin-bed mortar does not exceed 25 kg/m².

Reinforcement

With a material change in the plaster substrate, with insulation boards, etc., bed reinforcement mesh in the upper third of the plaster layer with at least 100 mm joint overlap and 200 mm overlap on all sides to the flanking component. The plaster is applied wet-in-wet in two layers, whereby the first layer has not yet started to set on the surface when the 2nd layer is applied.

Application time

Up to about 180 minutes depending on the plaster substrate.

Application temperature / climate

Do not apply material at air and/or substrate temperatures below +5 °C and above +30 °C.

Cleaning

Clean the machines and tools with water immediately after use.

Product description**Coatings**

The plaster must be dry, free of loose bits and dust-free for all coatings and linings.

Apply primer to suit the subsequent paints/coatings/linings, generally a deep primer. Apply a wallpaper paste layer to the wall for wallpapers.

Fire protection enhancement**Without plaster base (up to 15 mm plaster thickness)**

A 10 mm thick plaster layer is equivalent to 10 mm of normal concrete used for the concrete cover of the reinforcement. Pretreatment with rough cast is necessary.

With non-combustible plaster base

A non-combustible plaster base is required for plaster thickness \geq 15 mm to 25 mm. Here 8 mm thick plaster with a plaster base is equivalent to 10 mm of normal concrete. The maximum plaster thickness on the plaster base is 20 mm. The plaster must penetrate the coarse meshed plaster base by \geq 10 mm and with ribbed expanded metal by \geq 5 mm.

Technical specifications

Description	Standard	Unit	Value
Reaction to fire	ISIRI 12015-1	Class	A1
Flexural strength	ISIRI 12015-1	N/mm ²	≥ 1.0
Compressive strength	ISIRI 12015-1	N/mm ²	≥ 2.0
Thermal conductivity λ10,dry,mat	ISIRI 12015-1	W/(m·K)	0.26
pH value	-	-	13
Dry density	-	kg/m ³	approx. 800

The stated technical data were evaluated acc. to the respective test standards. Deviations under site conditions are possible.

Material requirement and efficiency

Coat thickness mm	Consumption approx. kg/m ²	Yield approx. m ² /bag	m ² /t
10.0	10	3	100

The exact consumption can only be determined with a test application on the individual object.

Packaging

Product	Weight (kg)	Packaging (pcs./pallet)	Material Number
MP ULTRA	30	40	7024333002

Kplus Direct: Technical Support Dept.

- ▶ Phone: (+98 21) 88207929
- ▶ Fax : (+98 21) 88203126
- ▶ technical@kplusi.ir

All technical changes reserved. Only the current printed instructions are valid. Our warranty is expressly limited to our products in flawless condition. All application quantities and delivery amounts are based on empirical data that are not easily transferable to other deviating areas. The stated information represents current state-of-the-art Kplus technology. The entire state of approved engineering rules, appropriate standards, guidelines, and rules of craftsmanship are not included herewith. These and all application instructions have to be adhered to separately by the installer.

All rights reserved. All amendments, reprints and photocopies, including those of excerpts, require the express permission of Kplus.

Head Office:

No. 19, East Qobadian Alley, Nelson Mandela (Africa) Blvd., 19176-34611, Tehran, Iran